

ABSTRACT OF THE DISCLOSURE

A tantalum oxide film is formed on a lower conductive film by vapor-deposition, and then is treated with active oxygen species. The treated film is annealed at a temperature lower than the crystallization temperature of tantalum oxide by 10 to 80°C in an inert atmosphere. Subsequently, an upper conductive film is formed on the annealed tantalum oxide film.